

How many grams of pigment should be used for 1 kg of Microcement BASE, 1 kg Microcement DECK and 1kg Microcement FINE			
PIGMENT/ COLOUR	Usage of ClaudiCemento Pigment per 1 kg ClaudiCemento Microcement BASE	Usage of ClaudiCemento Pigment per 1kg ClaudiCemento Microcement DECK	Usage of ClaudiCemento Pigment per 1kg ClaudiCemento Microcement FINE
1.White	25.00 grams	26.09 grams	30 grams
2. Light grey	3.88 grams	4.04 grams	4.65 grams
3. Grey	6.25 grams	6.52 grams	7.5 grams
4. Medium grey	10.21 grams	10.65 grams	12.25 grams
5. Dark Grey	46.88 grams	48.91 grams	56.25 grams
6. Olive	7.92 grams	8.26 grams	9.5 grams
7. Beige	6.25 grams	6.52 grams	7.5 grams
8. Pearl	10.42 grams	10.87 grams	12.5 grams
9. Terracotta orange	23.33 grams	24.35 grams	28 grams
10.Carrot orange	29.17 grams	30.43 grams	35 grams
11. Brown	58.13 grams	60.65 grams	69.75 grams
12. Camel	25.00 grams	26.09 grams	30 grams
13. Peach	13.54 grams	14.13 grams	16.25 grams
14. Aqua	4.58 grams	4.78 grams	5.5 grams
15. Sunflow	5.00 grams	5.22 grams	6 grams
16. Coral	12.08 grams	12.61 grams	14.5 grams

17. Chestnut	27.50 grams	28.70 grams	33 grams
18. Mint	91.88 grams	95.87 grams	110.25 grams
19. Citron	9.58 grams	10.00 grams	11.5 grams
20. Pacific blue	25.00 grams	26.09 grams	30 grams
21. Light purple	65.00 grams	67.83 grams	78 grams
22. Sand	7.42 grams	7.74 grams	8.9 grams
23. Vanilla	2.71 grams	2.83 grams	3.25 grams
24. Latte	18.75 grams	19.57 grams	22.5 grams
25. Baby Pink	14.83 grams	15.48 grams	17.8 grams
26. Lilac	11.88 grams	12.39 grams	14.25 grams
27. Mustard	33.75 grams	35.22 grams	40.5 grams
28. Coffee	33.71 grams	35.17 grams	40.45 grams
29. Orange	37.50 grams	39.13 grams	45 grams
30. Pink	2.50 grams	2.61 grams	3 grams
31. Hunter green/Black	93.75 grams	97.83 grams	112.5 grams
32. Lemon	35.63 grams	37.17 grams	42.75 grams
33. Scarlet	35.25 grams	36.78 grams	42.3 grams
34. Red	37.50 grams	39.13 grams	45 grams
35. Sandy brown	18.75 grams	19.57 grams	22.5 grams
36. Baby blue	29.75 grams	31.04 grams	35.7 grams
37. Deep sea blue	126.25 grams	131.74 grams	151.5 grams

38. Jasmine	13.96 grams	14.57 grams	16.75 grams
39. Sky blue	8.63 grams	9.00 grams	10.35 grams
40. Gold	25.00 grams	26.09 grams	30 grams

One bottle of ClaudiCemento pigment is ready to be mixed with one 20kg bucket of ClaudiCemento Microcement Fine, one bucket 23kg bucket of ClaudiCemento Microcement Deck, or one 24kg bucket of ClaudiCemento Microcement Base.

If less than a full bucket of microcement Deck, Fine or Base is used, then we need to calculate how much pigment should be added.

The calculation is as follows:

Weight of the pigment divided by the weight of the product, for example:

One bottle of Light Grey pigment is 93 gr.

Therefore, 93gr of Light Grey should be mixed with a full bucket of Microcement Fine (20kg), Deck (23kg) or Base (24kg).

If we wish to use only 5kg of Microcement Fine then we need to divide 93gr by 20kg and multiply it by 5kg (by the actual weight of the product that we will be using)

$93\text{gr} : 20\text{kg} = 4.65\text{gr}$ (this is how much we would use of 1 kg of Microcement Fine)

$4.65\text{gr} \times 5 = 23.25\text{gr}$

For 5kg microcement Fine we need 23.25gr of ClaudiCemento Light Grey pigment